

Crimp specification				
Type Document Crimp Specification Revised /Edition A1				
Date Issued:	2022/09/02			
Subject:3535TH			Issued By:	
2.00mm Pitch Terminal crimp specification			Engineering Dept.	

Description:


Height and width of conductor crimp core should be set as required.

(conductor crimp height and width of conductor barrel)

According to the external diameter and the type of electric wire, the width of crimped sheath shall be adjusted, wire won't be easily taken off from contact nor too much crimped.

(Crimped width of insulation barrel)

Position Graph:



Note:

- 1. Conductor crimp width. W1
- ${\it 2. Conductor\ crimp\ height.\ H1}$
- 3. Insulator crimp width. W2
- 4. Insulator crimp height. H2
- 5. Conductor wire shall be dimension long (mm) out A.
- 6. Naked part of sheathed wire must be located in the vicinity of center B.
- 7. The Crimp mouth must be equipped like bell.



Crimp specification						
Type Document	Type Document Crimp Specification Revised /Edition A1					
Date Issued:	Date Issued: 2020/07/09 Data Revised: 2022/09/02					
Subject:3535TH	Issued By:					
2.00mm Pitch Terminal crimp specification			Engineering Dept.			

Requirement:

	Subject:FLRY-A or equivalent type electric wire						
AWG#	Conductor (mm²)	Insulation Diameter	Insulator skins length (Dim .B) mm	Copper wire leakage size (Dim .A) mm	Dim. L1 (mm) out		
#22~#20	0.35mm~0.50mm²	1.30mm~1.45mm	0.30mm~0.70mm	0.20mm~0.50mm	1.40mm~1.70mm		
Wire Gauge	e Gauge Conductor Crimp Area		Insulator Crimp Area -		Terminal Tensile		
(AWG#)	Width (W1)	Height(H1)	Width (W2)	Height(H2)	Strength		
0.35mm ²	1.35±0.03mm	0.76±0.03mm	1.60±0.05mm	1.65±0.05mm	50N		
0.50mm ²	1.33±0.0311111	0.84±0.03mm	1.00±0.05IIIII	1.70±0.05mm	60N		

Remarks

- 1. Unalike equipment and crimp reel molds skill facility or not shall be difference to result in dissimilar.
- 2. This crimping specification is not limited to material changes.

Signature: _	Feng Xing	ENG
Donaguan SE.	SO Technology Co	oLtd



Crimp specification					
Type Document					
Date Issued:	2022/09/02				
Subject:3535TH			Issued By:		
2.00mm Pitch Terminal crimp specification			Engineering Dept.		

Date	REV	DESCRIPTION	MODIFY	APPROVAL
2020/07/09	А	Initial Issued	/	Kim Huang
2022/09/02	A1	Modify the dimensions of H1 and W1	Feng Xing	Kim Huang



Crimp specification					
Type Document					
Date Issued:	2022/05/19				
Subject:3535T	Issued By:				
2.00mm Pitch Terminal crimp specification			Engineering Dept.		

Description:


Height and width of conductor crimp core should be set as required.

(conductor crimp height and width of conductor barrel)

According to the external diameter and the type of electric wire, the width of crimped sheath shall be adjusted, wire won't be easily taken off from contact nor too much crimped.

(Crimped width of insulation barrel)

Position Graph:



Note:

- 1. Conductor crimp width. W1
- 2. Conductor crimp height. H1
- 3. Insulator crimp width. W2
- 4. Insulator crimp height. H2
- 5. Conductor wire shall be dimension long (mm) out A.
- 6. Naked part of sheathed wire must be located in the vicinity of center B.
- 7. The Crimp mouth must be equipped like bell.



Crimp specification					
Type Document					
Date Issued:	2022/05/19				
Subject:3535T	Issued By:				
2.00mm Pitch Terminal crimp specification			Engineering Dept.		

Requirement:

	Subject:UL1061 or FLRY-A equivalent type electric wire					
AWG#	Conductor (mm²)	Insulation Diameter	Insulator skins length (Dim .B) mm	Copper wire leakage size (Dim .A) mm	Dim. L1 (mm) out	
#26~#24	0.128mm~0.22mm²	1.00mm~1.40mm	0.30mm~0.70mm	0.20mm~0.50mm	1.40mm~1.70mm	
Wire Gauge	ire Gauge Conductor Crimp Area Insulat		Insulator C	rimp Area	Terminal Tensile	
(AWG#)	Width (W1)	Height(H1)	Width (W2)	Height(H2)	Strength	
#26	1.02±0.02mm	0.59±0.03mm	1.45±0.05mm	1.30±0.05mm	13.7N	
0.22mm ² 1.02±0.03mm	0.67±0.03mm	1.40±0.05HIIII	1.40±0.05mm	40N		

Remarks

- 1. Unalike equipment and crimp reel molds skill facility or not shall be difference to result in dissimilar.
- 2. This crimping specification is not limited to material changes.

Signature: 7% ENG

Dongguan SESO Technology Co.,Ltd